

<b>Product Code</b>	AKPEROX BP50 PASTE
<b>Description</b>	DiBenzoyl Peroxide, Paste, 50% in plasticizer. Produced in white and red colors. Different colors can be produced if requested
<b>Specifications;</b>	
Density (@25°C)	: 1,10 - 1,14 gr/cm <sup>3</sup>
Appearance	: In Red and White Colors, in paste form
Active Oxygen Content	: 3,1% –3,4%
Peroxide Content	: 49,0% –51,0%
SADT	: 50°C
CAS Nr	: 94-36-0
EINECS/ELINCS Nr	: 202-327-6
UN Nr	: UN 3108
<b>Applications</b>	AKPEROX BP 50 is used for curing unsaturated polyester (UP) resin based polyester putties, marble and stone adhesives.
<b>Usage &amp; Amount</b>	Recommended to use 1% – 3% in general, according to climate conditions and product formulation. In order to obtain longer workable time, amount of usage should be reduced. It is usable with Amine and Cobalt accelerators.
<b>Packaging</b>	25 gr, 40 gr and 60 gr in tubes 30 kgs PE Drum Different packages can be produced if requested
<b>Handling &amp; Storage</b>	Recommended storage temperature is between +5 C and +30 C. Keep pails tightly closed. Store and handle in a dry, well-ventilated place. Keep away from sources of heat, ignition and direct sunlight in original packaging. Provide grounding and venting in order to prevent static electricity build-up. Avoid any contact with Amine and Cobalt Accelerators, acids, alkalis and heavy metal compounds such as driers and metal soups.
<b>Shelf Life</b>	6 Months For unopened packages at recommended storage conditions

