



אלמור פיברגלס יבוא יצוא 1996 בע"מ

PS-10 (51 / 53)

Paraffin solution in styrene monomer			
<i>Properties as supplied</i>	<i>Unit</i>	<i>Test Method</i>	<i>Value</i>
Viscosity at 25°C, Brookfield RVT, 100 rpm	cps	ISO 2555	10 ± 5
Monomer content	%	ISO 3251	90 ± 1
Density;	g/cm ³	ISO 1675	0.9 ± 0.05
Solidification temperature	°C	ILK-TL-06	22 ± 1

Storage life _____ : Min 6 months (20 °C in darkness) Storage life decreases with increasing temperature. Avoid exposure to heat sources such as direct sunlight, steam pipes, heaters, etc. Rotate stock to ensure use within six months.

Packing _____ : 17 Kg net, 18.4 Kg gross, tins.

Field of application _____ : PS-10 is recommended for preventing surface adhesion at polyester resins.