

TECHNICAL DATA

ETERSET 3030 RESILIENT LAMINATE POLYESTER RESIN

ETERNAL CHEMICAL CO., LTD.

2013/12/04

Resilient Polyester Resin for Hand Lay-up

Description:

ETERSET 3030 is a thixotropic, prepromoted resilient polyester containing no wax.

Performance:

Offers high impact strength.

Provides medium-fast cure.

Gives good wet-out.

Has good strength in laminates.

Has medium thixotropic index.

Suggested Uses:

General purpose hand lay-up of small parts.

SPECIFICATIONS

Appearance	Pink turbid
Styrene monomer content, %	37.5 - 41.5
Viscosity (Brookfield spindle #3, 60rpm, at 25° C), cps	350 - 450
Thixotropic index (Brookfield spindle #3, 6/60rpm, at 25° C)	1.0 - 2.0
Acid value, mg KOH/g resin	17 - 27

TYPICAL PERFORMANCE DATA

(for guidance only)

Typical Curing Characteristics:

Room temperature cure at 25° C, 1.0% MEKPO (55%) Gel time, mins. 17 Total time to peak exotherm, mins. 29 Peak exotherm temperature, $^{\circ}$ C 150

Typical Physical Properties:

Clear casting, ETERSET 3030	
Barcol (934-1) hardness	41
Tensile strength, kgf/mm ² (ASTM D 638)	6.0
Elongation, %(ASTM D 638)	2.3
Flexural strength,kgf/mm ² (ASTM D 790)	11
Flexural modulus,kgf/mm ² (ASTM D 790)	300
Heat deflection temperature, $^{\circ}\text{C}$	67
Glass Fiber Laminates (450g/m ² 3 layers)	
Tensile strength, kgf/mm ² (ASTM D 638)	11.6
Flexural strength,kgf/mm ² (ASTM D 790)	17.6
Flexural modulus,kgf/mm ² (ASTM D 790)	730
Fiber content, %	30

Recommended Storage:

Typical storage life at temperature below 25°C is three months. Storage life decreases with increasing temperature. Avoid exposure to heat sources such as direct sunlight or steam pipes. Keep containers sealed to prevent moisture pick-up and monomer loss. Agitate before using.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty negligence, or otherwise is limited to the purchase price of the material